


**Material:** 2-6mm Granite  
**Source:** Bourne Amenity Ltd  
**Date:** 10/02/2020  
**Tested Against:** PD6682-1 BS EN 1620:2020+A1 Table C.1  
**Tested By:** XtraTec Ltd (Report ID XTE47153)

Sieve Size	Percent Passing	Sieve Size	Percent Retained
10mm	100	14-10mm	0
8mm	100	10-8mm	0
6.3mm	98	8-6.3mm	2
4mm	56	6.3-4mm	42
2mm	10	4-2mm	46
1mm	4	2-1mm	6
0.5mm	3	1-0.5mm	1
0.25mm	2	0.5-0.25mm	1
0.125mm	2	0.25-0.125mm	0
0.063mm	1.4	0.125-0.063mm	0.6
		<0.063	1.4

Water Content (%)	3.8
-------------------	-----



**Bourne Amenity Ltd, The Wharf, Rye Road, Newenden, Kent TN18 5QG**

01797 252299 • enquiries@bourneamenity.co.uk

www.bourneamenity.co.uk

VAT No: 863 1196 22 • Registered in England No: 3453821