

Material: Grade C Sand
Source: Bourne Amenity Ltd
Date: 2018
Tested Against: USGA Guidelines
Tested By: In-House

| Parameter | Guide | Range | | Feb 2018 Result | March 2018 Result | April 2018 Result | June 2018 Result |
|-------------------|-----------------|-------|------|-----------------|-------------------|-------------------|------------------|
| Texture: | | | | | | | |
| Stones and Gravel | >3.4mm | 0 | | 0.0 | 0.0 | 0.0 | 0.0 |
| Fine Gravel | >2.0mm | ≤ 3 | ≤ 10 | 0.7 | 0.9 | 0.8 | 1.2 |
| Very Coarse Sand | 2.0 - 1.0mm | | | 3.9 | 4.0 | 2.9 | 4.8 |
| Coarse Sand | 1.0 - 0.5mm | ≥ 60 | | 12.5 | 13.6 | 11.9 | 15.9 |
| Medium Sand | 0.5 - 0.25mm | | | 52.3 | 51.9 | 53.9 | 48.0 |
| Fine Sand | 0.25 - 0.15mm | ≤ 20 | | 23.3 | 21.5 | 21.9 | 21.0 |
| Very Fine Sand | 0.15 - 0.053mm | ≤ 5 | ≤ 10 | 3.9 | 3.8 | 2.1 | 3.8 |
| Silt | 0.053 - 0.002mm | ≤ 5 | | 3.7 | 4.3 | 6.5 | 5.3 |
| Clay | <0.002mm | ≤ 3 | | | | | |